





中国认可 国际互认 检测 TESTING CNAS L4743

Test Report

No. AJFS1910010829FF

Date: NOV.22, 2019

Page 1 of 6

NS PLAKAT DOO NOVI SAD

ZRENJANINSKI PUT 8, NOVI SAD, SERBIA

The following sample(s) was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion. results apply to the sample as received.

Sample Description: FABRIC FOR UV/ECO - SOLVENT PRINT

Color: WHITE

Composition: 100% POLYESTER

Style/Item No.: U/SZB-1

Manufacturer: HAINING TIANCHENG WARP KNITTING FABRIC CO., LTD

End Use Application: ADVERTISING

Addition Information: WEIGHT: 110±5 GRAM / SQM

Test Requested:

To determine the flammability (building materials class B1) in accordance with DIN 4102-1 (May 1998) Fire behaviour of building materials and elements Part 1: Classification of building materials, Requirements and testing

Test Results: -- See attached sheet -

<u>Classification</u>: The tested sample **meets** class **B1** building materials requirements of DIN 4102-1 (May 1998).

Test Period:

Sample Receiving Date : NOV.05, 2019

Test Performing Date : NOV.05, 2019 TO NOV.20, 2019

Signed for and on behalf of SGS-CSTC Co., Ltd. Anji Branch

Allen Zou Lab Manager



AJFS1910010829F



Unless otherwise agreed in writing, inits accument is issued by the Company sub-clothed properties of the Company and Conditions, aspect and Conditions of Service printer subject to Terms and Conditions of accessible at http://www.sgs.com/en/Terms-and-Conditions, aspect and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-a-Document aspect at terms and the conditions for the Company in Indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company is findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sol responsibility is to its Client and this document does not exonerate parties to transaction from exercising all their rights and obligations under the transaction documents. This document can be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forery or falsification of the content of appearance without prior written approval of the Company. Any unauthorized alteration, forery or falsification of the content of appearance without prior written approval of the Company and the content of appearance without prior written approval of the Company and the content of appearance without prior written approval of the Company and the content of appearance without prior written appearance with the content of the content o

1443, or email: CN.Doccheck@sgs.com

|No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018826 f (86-572) 5018826 g www.sgsgroup.com.cn
中国・浙江・安吉县阳光工业関二区阳光大道301号 邮编:313300 t (86-572) 5018826 f (86-572) 5018826 e sgs.china@sgs.com



No. AJFS1910010829FF

Date: NOV.22, 2019

Page 2 of 6

I. Test conducted

This test was conducted as per DIN 4102-15:1990 DIN 4102-16:1998 and DIN 4102-1:1998 Clause 6.2, and Classification in according to DIN 4102-1 (May 1998) Clause 6.1-Class B1 materials.

II. Sample details

General description	Fabric
Color	White
Area Density	116 g/m ²
Size of sample	190mm×1000mm & 190mm×90mm

Conditioning

Prior to testing, the sample was conditioned at least 14 days to constant mass at a temperature of 23 ± 2 $^{\circ}$ C, and a relative humidity of 50 ± 6 %.

III. Test results

1) "Brandschacht" Test according to DIN 4102-15 &16

Exposed surface: The coated surface

Results of "Brandschacht" Test (part 1)							
Line		Unit	Test assemblies No.				
No.			Lengthwise	Widthwise			
1	Specimen fixings according to DIN 4102 part 15, table	1	1	1			
2	Max. flame height above lower sample edge;	cm	40	40			
3	Time 1)	min:s	0:29	0:34			
	Melting/burning through		1	1			
4	Time 1)	min:s	0:05	0:04			
	Back of specimen		/	1			
5	Flaming/glowing, Time 1)	min:s	0:06	0:05			
6	Discolouring, Time 1)		0:02	0:02			
	Burning droplets		No	No			
7	Begin 1)	min:s	/	/			
	<u>Amount</u>		/	/			
8	Specimen material falling off in separate droplets		/	/			
9	Specimen material falling off continuously		/	/			

To be continued...



No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn



No. AJFS1910010829FF

Date: NOV.22, 2019

Page 3 of 6

	Results of "Brandscha	acht" Tes	t (part 2)			
Line		Unit	Test assemblies No.			
No.		Onit	Lengthwise	Widthwise		
	Burning parts		No	No		
10	Begin 1)	min:s	/	1		
11	Parts of sample falling off separately		/	/		
12	Parts of sample falling off continuously		1	1		
13	Duration of continued combustion on mesh base (max.)	min:s	No	No		
	Burner flame impairment by dripping/falling material		No	No		
14	Time 1)	min:s	1	/		
	Premature ending of test		/	1		
15	End of burning at specimen 1)	min:s	/	1		
16	Time when test terminated (if applicable) 1)	min:s	/	1		
	Burning after end of test		No	No		
17	Duration	min:s	/	1		
18	Number of specimens		1	1		
19	Front of specimen		/	/		
20	Back of specimen		/	1		
21	Height of flame	cm	1	1		
	Glowing after end of test		No	No		
22	Duration	min:s	/	/		
23	Number of specimens		/	/		
24	Front of specimen		/	/		
25	Back of specimen		1	/		
26	Top half of specimen		/	/		
27	Bottom half of specimen		/	/		

To be continued...



| No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 | t (86-572) 5018825 f (86-572) 5018829 | www.sgsgroup.com.cn |
中国・浙江・安吉县阳光工业园二区阳光大道301号 | 邮编:313300 | t (86-572) 5018825 f (86-572) 5018829 | e sgs.china@sgs.com



Test Report No. AJFS1910010829FF Date: NOV.22, 2019 Page 4 of 6

Results of "Brandschacht" Test (part 3)								
Line		Unit	Test assemblies No.					
No.).		Lengt	hwise	Widthwise			
	Residual length		1		1			
28	Single results	cm	72 71	70 70	73 71	73 72		
29	Average of the single results	cm).8	72.3			
	Smoke temperature		/		/			
30	Max. of average	$^{\circ}\mathbb{C}$	125.4		124.1			
31	Time 1)	min:s	9:26		9:45			

Note: 1) time from start of testing

Class B1 materials:

If the residual length measured after the first test is 45cm or greater, further tests are not required.

2) Normal Flammability Test according to DIN 4102-1 Clause 6.2

Edge ignition

Fire application time: 15s

Doromotor	Lengthwise					Crosswise				
Parameter		2	3	4	5	6	7	8	9	10
Whether or not flaming extinguished before reach the gauge mark(Yes/No)	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes
Whether or not flaming reach the measuring mark within 20 seconds (Yes/No)	No	No	No	No	No	No	No	No	No	No
Time for the flame tip to reach the gauge mark(s)	NA	NA	NA	NA	NA	NA	NA	NA	NA	NA
Afterflame time (s)	0	0	0	0	0	0	0	0	0	0
Max. flame height (cm)	4	6	6	5	4	5	6	6	4	3
Molten dripping (Yes/No)	No	No	No	No	No	No	No	No	No	No
Smoke developments (visual impression)	Slight Slight									

Note:

NA---Not applicable

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-end-Conditions.appx and, for electronic Documents at http://www.sgs.com/en/Terms-e-Document.aspx. Associated in the limitation of liability, indemnification and jurisdiction is used earlier. Any holder of this document is extended in the second of the second in the second

1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Blook, Sunlight Industry Zone, Anji County, Zhejang Province, China 313300 t (86-572) 5018825 f (86-572) 5018825 mwww.sgsgroup.com.cn 中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

^{*}Reduction in number of test (DIN 4102 Part 16, clause 5.2)



No. AJFS1910010829FF

Date: NOV.22, 2019

Page 5 of 6

IV. DIN 4102-1:1998 Criteria for classification

- 1) All materials, except flooring, may be classed as **B1** materials if they meet the following requirements a) and b):
- a) The test using the 'Brandschacht' apparatus described in DIN 4102-15 (cf. subclause 6.1.3.1) shall be deemed passed if
- The mean value for the residual length (portion of specimen that has not burned or charred; cf. subclause
- 9.1 of DIN 4102-16) of each specimen is at least 15 cm and no individual values are lower than 0 cm,
- The mean effluent temperature does not exceed 200 °C in any test,
- The requirement for the residual length of each specimen is met even where there is afterflame, afterglow, or smouldering.
- b) Pass DIN 4102-1: 1998 sub-clause 6.2.3 Ignitability Test if

For each specimen, flaming doesn't reach the gage mark within 20s after flame application.

 Materials may be classed as B2 materials if they pass the ignitibility test specified in DIN 4102-1: 1998 subclause 6.2.5.

For each specimen, flaming doesn't reach the gage mark (150mm marks) within 20s after flame application.

3) Combustible materials which cannot be classed as B1 or B2 materials shall be classed as B3 materials.

STATEMENTS:

This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.

This test report does not replace any mandatory certification of the product that may be required.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire and smoke hazard of the product in use.

To be continued...





No. AJFS1910010829FF

Date: NOV.22, 2019

Page 6 of 6

Photo Appendix:



SGS authenticate the photo on original report only

*** End of Report ***



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at https://www.sgs.com/en/Team-and-Conditions/Team-and-

Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 830: 1443, or email: CN Doccheck@sqs.com

No.301, Suright Road, 2 Block, Suright Adayt Zone, Apri County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572)